

DARING - Technical specifications

ISO 13006 - EN 14411 - ISO 10545 Standards

Nominal sizes (cm): 15x61; 24x120; 24x150; 26.5x180	Thickness (mm) : 8.5 (24x120 ,26.5x180, 24x150) 6.5 (15x61) – 9 (15x61 strong) ;
Sides: Non- rectified (15x61 , 24x120) Rectified (26.5x180)	Surface: matt, strong/grip
	Product Group: Bla-GL

Technical characteristics		Test method	EN 14411 and ISO 13006 requirements	Italcer Average values	
Dimensions	Length and width	ISO 10545-2	±0.6% and ± 2.0mm	Compliant	
	Straightness of sides	ISO 10545-2	±0.5% and ± 1.5mm	Compliant	
	Rectangularity	ISO 10545-2	±0.5% and ± 2.0mm	Compliant	
	Flatness	ISO 10545-2	±0.5% and ± 2.0mm	Compliant	
	Thickness	ISO 10545-2	±5% and ± 0.5mm	Compliant	
Water absorption		ISO 10545-3	≤ 0.5%	<0.15%	
Modulus of rupture		ISO 10545-4	≥ 35 N/mm ²	>50 N/mm ²	
Breaking strength (S)		ISO 10545-4	≥ 1300 N ≥ 700 N (15x61 slim)	Compliant	
Abrasion resistance		ISO 10545-7	Declared class	PEI 5 (Ivory) PEI 4 , PEI 3 (Dark)	
Linear thermal expansion		ISO 10545-8	Declared value	$\alpha \leq 7.1 \times 10^{-6} \text{ } ^\circ\text{C}^{-1}$	
Thermal shock resistance		ISO 10545-9	No alterations	Resistant	
Frost resistance		ISO 10545-12	No alterations	Resistant	
Chemical resistance		ISO 10545-13	Declared value	LA – HA	
Household chemicals resistance		ISO 10545-13	B min.	A	
Stain resistance		ISO 10545-14	Class 3 min.	5	
Mohs Hardness		UNI EN 101	5 Min.	7	
				Natural	Strong / Grip
Slip Resistance		DIN 51130	Declared value	R10	R11
		DIN 51097	Declared value	B	C
		ANSI A137.1	Declared value	>0.42	>0.42
		B.C.R.A. Rep. CEC/81	Declared value	>0.4	>0.4
		BS 7976	Declared value	Dry : >36 Wet : 25<x<35	Dry/Wet : >36
Shade variation		ANSI A 137.1	Not required	V3	
Fire reaction		UNI EN 13501-1	-	A1 _{FL} class	
Thermal Conductivity		EN 12524	Not required	$\lambda = 1.3 \text{ W/m}\cdot\text{K}$	
Light and colour fastness		DIN 51094	Not required	No variations	